




Journal of Innovative Solutions for Eco-Environmental Sustainability

journal homepage: <https://journals.ysu.am/index.php/jisees>



Review Article

Recent Advancement in Bioremediation of Pollutants Using Green Synthesized Nanoparticles

Priyanka Vashistha^{1*}, Dileep Kumar², Vandita Anand², Rajni Rani¹

¹DAV College for Girls, Yamuna Nagar, Kurukshetra University, Haryana, India

²Khawaja Moinuddin Chisti Language University, Lucknow, India

ARTICLE INFO

Keywords:

nanoparticles;
heavy metals;
bioremediation;
wastewater;
green synthesis

ABSTRACT

Advancements in agricultural approaches, increased population and industrial development have created the problem of environmental pollution. This pollution causes loss of biodiversity and several serious health diseases. Therefore, several approaches have been utilized to remove environmental pollution. However, most of these methods have drawbacks. Nanotechnology is an extensively growing field that has various applications in decreasing the adverse effects of toxic pollutants. Nanotechnology is a cost-effective and environmentally friendly method to solve the problem of environmental pollution. Nanoparticles (NPs) have been synthesized by traditional chemical and physical techniques. However, these traditional methods have several drawbacks, such as being expensive and producing toxic substances. The natural bioremediation method removes pollutants at a slow rate, and thus the removal process takes more time. Thus, it is important to introduce alternate techniques, which is nanobioremediation. Nanobioremediation includes the role of both microorganisms and NPs; as a result, the removal of pollutants by this method occurs within a shorter time. Biogenic resources such as bacteria, fungi, viruses, algae, yeast and plants are used to synthesize NPs. Biogenic method for the synthesis of NPs is a clean, safe, environmentally gentle, and sustainable method. The objective of the present review is to highlight the application of green synthesized NPs for the removal of pollutants such as dyes and heavy metals from wastewater. However, more research is required to study the toxic effects of green synthesized NPs, reusability and their commercialization on a larger scale. It is expected that the use of green-synthesized NPs for the removal of pollutants will expand in the future.

1. Introduction

Environmental pollution is becoming one of the major problems due to increasing population, urbanization, agricultural advancement and growth of industries. The main environmental contaminants include heavy metals, chemical insecticides, fertilizers, effluents released from industries and sewage. These contaminants are released into rivers and oceans, causing contamination and harmful effects on humans and aquatic animals [1]. The extreme use of synthetic dyes in various industrial activities and the utilization of chemical pesticides in agricultural fields is causing water and soil pollution. The removal of heavy metals and harmful substances from wastewater has become a major worldwide challenge [2, 3, 4]. Thus, conventional methods such as landfill techniques and capping, etc., are used for

removing the pollutants from water and soil. These techniques are temporary and they only work for a short time. A more effective method for degrading pollutants than traditional approaches is dechlorination, which can be catalyzed by a base, by UV oxidation, or achieved through high-temperature incineration. These techniques efficiently decrease the amount of several contaminants. However, they have several disadvantages such as being expensive, highly complex and having enhanced exposure to workers. Therefore, to combat this problem, bioremediation was used as an alternative method [5].

Bioremediation is a technique that uses living microorganisms to remove or neutralize different types of contaminants. These micro-organisms and plants convert hazardous and toxic pollutants into less toxic forms.

* Corresponding authors.

Email: priyankabiotech66@gmail.com

<https://doi.org/10.46991/JISEES.2026.02.1.13684>

Received 21 September 2025; Received in revised form 17 February 2026; Accepted 31 March 2026; Available online 12 July 2026

© 2026 The Authors. Published by YSU Publishing House

This is an open access article under the CC BY-NC-ND license (<http://creativecommons.org/licenses/bync-nd/4.0/>).




Figure 1. Conventional method for the synthesis of NPs [85]

Traditionally, various in situ and ex situ approaches for bioremediation of hazardous pollutants have been reported. These methods include biocomposting, biopiles, bioaugmentation, biostimulation, bioventing, landfarming and biosparging. However, these techniques have various drawbacks, such as the rate of growth and other technical factors. As a result, scientists have developed the field of nanobiotechnology to remove and degrade environmental pollutants [6].

Nanoparticles have a unique advantage as they contain more properties than their large counterparts [7] extensively. NPs are exceptional absorbents and catalysts, because of their larger specific areas, lower change in temperature, a greater number of related adsorption sites, and unique surface chemistry when compared to other options [8]. NPs that have a higher fraction of surface area, increased surface energy, precise dimensions, and spatial confinements are showing potential benefits in fields such as catalysis, magnetism, electronics, and optics [7]. There are various physical and chemical methods utilized for the synthesis of nanomaterials (Figure 1). Chemical methods involve the use of reduction and stabilizers, whereas physical methods utilize ball

milling and ultrasonication for the synthesis of NPs. Although most methods consume high amounts of energy, produce hazardous substances and are less sustainable and costly [9].

NPs are synthesized by either a top-down or a bottom-up technique.

In the top-down method, large structures are converted into small ones with the utilization of physical methods. The bottom-up method uses small atoms or molecules to synthesize NPs through self-assembly. Biological methods have gained more attention due to being environmentally friendly, consuming less energy and not producing any hazardous substances [10–13]. Micro-organisms in a polluted environment adjust and change themselves for the degradation of hazardous compounds having enough catabolic activity toward the contaminated environment [14]. Green synthesis of metal NPs has various benefits because of their physico-chemical characteristics and broad applications in the biotechnology field [15]. The main objective of the present review is to provide knowledge on recent developments in the bioremediation of pollutants using green synthesized NPs.

2. Green Synthesis of NPs

Green synthesis is an environmentally friendly method and alternative technique to the chemical method for the synthesis of NPs. The term “green synthesis” means the processes that prepared NPs with the less amount of energy consumption while preventing hazardous byproducts via cleanup, control, remediation, regulation and cleanup [16]. Bacteria are ubiquitous in the environment, occurring in soil, water and air. They can be easily grown under laboratory conditions. These characteristics make bacteria potential candidates for the synthesis of NPs. Bacteria is capable of manufacturing NPs both extracellularly or intracellularly [17]. Several NPs were synthesized from bacteria. Gold (Au) NPs were prepared from the marine bacteria *Marinobacter algicola* and *Paracoccus haeundaensis* [18,19]. Similarly, fungi are also easily cultured in high amount and rapidly synthesized NPs [20]. Various fungi were utilized for the synthesis of NPs. *Aspergillus niger* was utilized for the synthesis of CuNPs [21]. Algae were also used for the synthesis of various NPs. *Sargassum plagiophyllum* mediated the synthesis of AgCl NPs [22]. Several NPs were prepared from different forms of yeast. Ag and SeNPs were prepared by utilizing the extract of *Saccharomyces cerevisiae* [23–26]. Actinomycetes contain various secondary metabolites that can facilitate the synthesis of various NPs [27,28]. Various NPs were prepared from distinct types of actinomycetes. *Gordonia amarae* mediated the synthesis of AuNPs [29].

3. Methods for Green Synthesis of NPs

The synthesis of NPs using microbes and plants is fast, feasible, less expensive and eco-friendly [30]. The working principle of green synthesis of NPs includes bio-precipitation and reduction methods. These methods are carried out by amino acids, peptides, other bioactive compounds and polyphenols, which are released from living organisms [31]. These compounds work as a stabilizing agent. These compounds also prevent the mass formation of synthesized NPs [32]. Biosynthetic methods for NPs can be classified into three types intracellular, extracellular type of biosynthesis (according to the location where NPs are synthesized) and utilization of specific biochemicals [33]. Out of

both, the extracellular synthesis of NPs is more preferred due to simple down-stream processing and fast scale-up processing. The basic method for the synthesis of NPs involves the utilization of the intracellular and an extracellular extract of microorganisms and plants. Then the extract is mixed with metal salt solution at room temperature. The process is completed within few minutes. Figure 2 shows a picture of various microorganisms and plants used for the biosynthesis of NPs. The nature of the living extract, concentration of extract, the amount of the metal salt, the pH and temperature affect the speed of production of the NPs, their yield and other features [34].

4. Mechanism of Bioremediation

4.1 Adsorption Technique

Adsorption techniques are a commonly used method for treating polluted liquids. In this technique, metal ions are deposited on adsorbent surfaces to form a layer that consists of the ions and other contaminants. Compared to traditional methods for the removal of metal, adsorption has various benefits such as being cheaper, capacity for regeneration, less consumption of energy and chemicals, no production of sludge, and the ability for recovery of metal [35]. The performance of adsorption is affected by various factors involving as the quantity of adsorbent utilized, pH, the relations between the adsorbate and adsorbent, surface area of adsorbent, time required for contact, particle size, temperature and primary concentration of pollutant [36].

4.2 Photocatalytic Degradation

Photocatalytic degradation is a method that utilizes photocatalysts such as semiconductor materials, titanium dioxide (TiO₂), or zinc oxide (ZnO) to facilitate the degradation of pollutants under the influence of light. Upon irradiation with ultraviolet (UV) or visible light, photocatalysts generate electron–hole pairs, which can initiate oxidation and reduction reactions with surrounding molecules, such as water and dissolved oxygen. The use of photocatalysis, in particular, has gained attention because of its environmentally friendly nature, more efficient, cost-effective and ability to remove hazardous pollutants [37].




Figure 2. Mechanisms of synthesis of NPs from micro-organisms and plants [9]

5. Application of Algae-Based NPs for Bioremediation

Algae-based NPs have the potential of removing, degrading, or converting contaminants into less toxic or non-toxic forms, thus promoting nanoremediation [38, 39]. In a study, green silver (AgNPs) was synthesized using *Chlorella ellipsoidea* effectively removed the dyes such as methyl orange and methylene blue [40]. Fe₃O₄-NPs were produced using the species of brown macroalgae *Padina pavonica*, *Colpomenia sinuosa*, and *Petalonia fascia* reduced nitrogen and phosphorus-containing compounds from wastewater [41]. AgNPs and gold (AuNPs) were prepared from algae *Nannochloropsis* sp and *Chlorella vulgaris*. It has been observed that these algal NPs decreased the concentration of lead and zinc in wastewater [42]. *Sargassum latifolium* based AgNPs removed malachite green dye by bioadsorption process [43]. CdS NPs synthesized from blue green algae removed pollutants from wastewater [44]. Algae biofilm based FeONPs removed methylene blue (MB), malachite green (MG), and phenol red (PR) dyes [45]. In another study, *Pterocladia capillacea* based NPs increased bioremediation of toxic dyes [46].

5.1 Application of Bacteria-Based NPs for Bioremediation

AgNPs synthesized from *Macrococcus caseolyticus* and eliminated Total Petroleum Hydrocarbons in water samples [47]. Magnetite Fe₃O₄ and hematite Fe₂O₃ prepared from *Lyptolynghyafoveolarum* extract and *Azospirillumbrasileense* and removed ammonia, nitrate and phosphate from wastewater [48]. Platinum (Pt) and palladium (Bio-Pd) NPs synthesized using bacteria *Desulfovibrio vulgaris* removed various antibiotics from wastewater [49].

5.2 Application of Fungi-Based NPs for Bioremediation

It had been observed that fungi *Aspergillus niger* based AgNPs increased the bioremediation of diesel oil contaminated soil and water [50]. *Fusarium oxysporum* based CuO-NPs removed heavy metals and dyes from wastewater of textile industry [51]. *Fusarium oxysporum* based FeNPs had effectively removed various heavy metals (Zn, Cd, Pb, Cr and Ni) from wastewater [52]. Fe₃O₄ synthesized using *Aspergillus elegans* extract degraded dyes in wastewater with high efficiency [53]. In another study it was observed that TiO₂ NPs synthesized from *Aspergillus penicillioides* degraded crystal violet dye by the process of photocatalysis [54]. Similarly, ZnONPs synthesized using *Fusarium proliferatum* degraded anthracene [55]. Fungi based CuONPs and ZnONPs removed pollutants from

groundwater [56]. Magnetite NPs (Fe₃O₄) synthesized from the endophyte *Aspergillus flavus* reduced the toxicity of Reactive Black 5 (RB5) dye [57]. Iron oxide NPs synthesized from *Aspergillus niger* AUMC 16028 reduced heavy metals from industrial wastewater [58]. Fe₃O₄ NPs synthesized using *Aspergillus elegans* showed higher dye efficiency removal from wastewater [59].

5.3 Application of Plant-Based NPs for Bioremediation

AuNPs prepared from *Avicennia marina* 4-nitrophenol (4-NP) reduced into 4-aminophenol [60]. *Adenophora triphylla* extract based AuNPs degraded MB within 5 minutes of treatment and congo red in 10 minutes [61]. Bismuthoxide (BiO-NPs) prepared from almond gum reduced 4-nitrophenol to 4-aminophenol and degraded Congo Red and Brilliant Green dyes in wastewater [62]. CuONPs prepared from *Solanum tuberosum* degraded MB dye [63]. *Vaccinium floribundum* based FeNPs removed of 88.24% and 81.90% of petroleum hydrocarbons from contaminated water and soil [64]. FeNPs prepared from *Lawsonia inermis* is degraded hydrocarbon in crude oil [65]. FeONPs synthesized from *Ruellia tuberosa* degraded dyes from industrial and domestic wastewater [66]. Apple peel extract based FeNPs removed Cr and Pb [67]. Fe₂O₃ NPs synthesized from coconut pulp degraded Rhodamine B dye by the process of photocatalysis [68]. Spinach (*Amaranthus blitum*) based Fe₃O₄ NPs effectively removed Cu (98%) from wastewater [69]. Magnetite Fe₃O₄ and hematite Fe₂O₃ NPs were prepared from *Lyptolynghya foveolarum* and *Azospirillum brasiliense* and efficiently removed nitrate, phosphate and ammonia from wastewater [70]. rGO/MgO nanocomposite was synthesized from *Hylocereus polyrhizus* and degraded dyes in wastewater [71]. Tin oxide (SnO₂ NPs) synthesized from ginger extract degraded MB, methyl orange (MO), Eriochrome black-T (EB) and rhodamine B (RB) dyes in wastewater by photocatalytic process [72]. Titanium dioxide (TDO) NPs was synthesized from *durva* herb. TDO NPs degraded both Rh-B and MB dyes [73]. Zirconium (ZrO₂NPs) synthesized from *Phyllanthus niruri* degraded various dyes such as methemyl red, methyl orange, and MB [74]. ZnO NPs synthesized using *Ruellia tuberosa* degraded MB and malachite green dyes from textile industry wastewater [75]. ZnO and CuO NPs synthesized from *Serratula coronata* L. removed Pb(II) ion [76]. ZnO NPs synthesized from *Elettaria cardamomum* degraded MG dye in wastewater [77]. ZnO NPs prepared from extract of *Eucalyptus* leaf and effectively removed calcium ions (Ca²⁺) from groundwater [78]. ZnONPs synthesized using *Sesbania grandiflora* degraded crystal violet dye and decreased total solid content in glass industry wastewater [79].

Table 1. Recent examples of green synthesized NPs for bioremediation

Nanoparticles	Source	Application in Bioremediation	Ref.
Algae			
AgNPs	<i>Chlorella ellipsoidea</i>	Removed the dyes such as methyl orange and methylene blue	[40]
Fe ₃ O ₄ -NPs	<i>Padina pavonica</i> , <i>Colpomenia sinuosa</i> , and <i>Petalonia fascia</i>	Reduced nitrogen and phosphorus-containing compounds from wastewater	[41]
AgNPs	<i>Nannochloropsis</i> sp	Decreased the concentration of lead in wastewater	[42]
AuNPs	<i>Chlorella vulgaris</i>	Decreased the concentration of lead in wastewater	[42]
AgNPs	<i>Sargassum latifolium</i>	Removed malachite green (MG) dye	[43]
CdS NPs	Blue green algae	Removed pollutants from wastewater	[44]
FeONPs	Algae biofilm	Removed methylene blue (MB), MG and phenol red (PR) dyes	[45]
NPs	<i>Pterocladia capillacea</i>	Increased bioremediation of toxic dyes	[46]

Bacteria			
AgNPs	<i>Macrococcus caseolyticus</i>	Eliminated Total Petroleum Hydrocarbons in water samples	[47]
Magnetite Fe ₃ O ₄ and hematite Fe ₂ O ₃	<i>Lyptolyngbya foveolarum</i> extract and <i>Azospirillum brasilense</i>	Removed ammonia, nitrate and phosphate from wastewater	[48]
Platinum (Pt) and palladium (Bio-Pd) NPs	<i>Desulfovibrio vulgaris</i>	Removed various antibiotics from wastewater	[49]
Fungi			
AgNPs	<i>Aspergillus niger</i>	Increased the bioremediation of diesel oil contaminated soil and water	[50]
CuO-NPs	<i>Fusarium oxysporum</i>	Removed heavy metals and dyes from wastewater of textile industry	[51]
FeNPs	<i>Fusarium oxysporum</i>	Removed heavy metals from municipal wastewater	[52]
Fe ₃ O ₄	<i>Aspergillus elegans</i>	Degraded dyes in wastewater	[53]
TiO ₂ NPs	<i>Aspergillus penicillioides</i>	Degraded crystal violet dye	[54]
ZnO NPs	<i>Fusarium proliferatum</i>	Degraded anthracene	[55]
CuONPs and ZnONPs	Fungi	Removed pollutants from groundwater	[56]
Fe ₃ O ₄ NPs	<i>Aspergillus flavus</i>	Reduced the toxicity of Reactive Black 5 (RB5) dye	[57]
Iron oxide NPs	<i>Aspergillus niger</i>	Reduced heavy metals from industrial wastewater	[58]
Fe ₃ O ₄ NPs	<i>Aspergillus elegans</i>	Showed higher dye efficiency removal from wastewater	[59]
Plants			
AuNPs	<i>Avicennia marina</i>	Reduced 4-nitrophenol (4-NP) into 4-aminophenol	[60]
AuNPs	<i>Adenophoratriphylla</i>	Degraded MB and congo red (CR) dyes	[61]
Bismuthoxide (BiO-NPs)	Almond gum	Reduced 4-nitrophenol to 4-aminophenol and degraded CR and brilliant green dyes in wastewater	[62]
CuONPs	<i>Solanum tuberosum</i>	Degraded MB dye	[63]
FeNPs	<i>Vaccinium floribundum</i>	Removed of 88.24% and 81.90% of petroleum hydrocarbons from contaminated water and soil	[64]
FeNPs	<i>Lawsonia inermis</i>	Degraded hydrocarbon in crude oil	[65]
FeONPs	<i>Ruellia tuberosa</i>	Degraded dyes from industrial and domestic wastewater	[66]
FeNPs	Apple peel extract	Removed Cr and Pb	[67]
Fe ₂ O ₃ NPs	Coconut pulp	Degraded Rhodamine B dye	[68]
Fe ₃ O ₄ NPs	<i>Amaranthus blitum</i>	Removed Cu (98%) from wastewater	[69]
Magnetite Fe ₃ O ₄ and hematite Fe ₂ O ₃ NPs	<i>Lyptolyngbya foveolarum</i> and <i>Azospirillum brasilense</i>	Efficiently removed nitrate, phosphate and ammonia from wastewater	[70]
rGO/MgO nanocomposite	<i>Hylocereus polyrhizus</i>	Degraded dyes in wastewater	[71]
SnO ₂ NPs	Ginger extract	Degraded MB, methyl orange (MO), Eriochrome black-T (EB), and rhodamine B (RB) dyes in wastewater	[72]
TDO NPs	<i>durva</i> herb	Degraded both Rh-B and MB dyes	[73]
ZrO ₂ NPs	<i>Phyllanthus niruri</i>	Degraded various dyes such as methyl red, methyl orange, and MB	[74]
ZnO NPs	<i>Ruellia tuberosa</i>	Degraded MB and malachite green dyes from textile industry wastewater	[75]
ZnO and CuO NPs	<i>Serratula coronata</i> L.	Removed Pb(II) ion	[76]
ZnO NPs	<i>Elettaria cardamomum</i>	Degraded MG dye in wastewater	[77]
ZnO NPs	Extract of <i>Eucalyptus</i> leaf	Effectively removed calcium ions (Ca ²⁺) from groundwater	[78]
ZnONPs	<i>Sesbania grandiflora</i>	Degraded crystal violet dye and decreased total solid content in glass industry wastewater	[79]

6. Challenges of Green NPs in the Bioremediation Field

The green synthesis method for production of NPs as discussed earlier is cheaper, environmentally friendly, laborious, easy to use and shows high efficiency. Due to these properties, green synthesized NPs are preferred in various fields of environmental science [80]. Microbe-based NPs provide a better down-streaming process, also the growth of microbes is controllable and highly achievable in less time therefore green synthesis method is a better approach to get a clean, safe and biodegradable environment in no time [81]. Besides the various benefits of nanotechnology, many disadvantages are also observed. One of the main disadvantages of nanotechnology is the commercialization of NPs on a larger scale. Large scale-up production of green synthesized nanotechnology requires the long-term stability of capping and reducing agents [82] and reusability of NPs which after a few trials show decreased efficacy [83]. Synthesis of NPs also needed chemical substances and green synthesis technology needed high temperature, lack of knowledge in the NPs production, different extracts generate variable size of NPs which make them unfit for large scale-up production. The low yield of green synthesized NPs cause hinders in field of nanobiotechnology [84].

7. Conclusions and Future Prospects

Bioremediation applications are increased due to overpopulation and environment pollution. However, traditional methods of bioremediation have some technical disadvantages that can be overcome by using nanotechnology. Nanotechnology combined with microorganisms has provided a green method toward the bioremediation of hazardous pollutants. In future, the green synthesized NPs can simply separate and reuse due to their efficiency and more stability. Furthermore, the green synthesis of NPs for water and soil treatment is an environment-friendly and potential technology to accomplish the zero effluent release in wastewater treatment and soil effluents. Thus, green nanotechnology focuses on enhancing treatment techniques by raising the process efficiency and reusability can save the operation cost in soil treatment as well as water. Therefore, the green synthesized NPs are important components utilized to remediate the water and soil pollution in the environment. More research is needed to investigate the toxic effects of NPs when introduced into the environment. Additional research will also be required to study the effectiveness of green synthesized NPs in scale up remediation of pollutants from wastewater. By addressing these problems, biogenic NPs can provide a great solution for pollutant remediation.

Author Contributions

All the authors actively contributed to manuscript drafting.

Data Availability Statement

Not applicable.

Conflicts of Interest

The authors declare no conflict of interest.

References:

- Sharma, G.; Jasuja, N.D.; Kumar, M.; Ali, M.I. (2015). Biological Synthesis of Silver Nanoparticles by Cell-Free Extract of *Spirulina platensis*. *J. Nanotechnol.* 132675.
- Choi, S.; Johnston, M.; Wang, G.S.; Huang, C.P. (2018). A Seasonal Observation on the Distribution of Engineered Nanoparticles in Municipal Wastewater Treatment Systems Exemplified by TiO₂ and ZnO. *Sci. Total Environ.* **625**, 1321–1329.
- Doshi, B.; Sillanpaa, M.; Kalliola, S. (2018). A review of Bio-Based Materials for Oil Spill Treatment. *Water Res.* **135**, 262–277.
- Hu, X.; Ren, C.; Kang, W.; Mu, L.; Liu, X.; Li, X.; Wang, T.; Zhou, Q. (2018). Characterization and Toxicity of Nanoscale Fragments in Wastewater Treatment Plant Effluent. *Sci. Total Environ.* **626**, 1332–1341.
- Kensa, V.M. (2011). Bioremediation-An Overview. *J. Indust. Pollut. Cont.* **27**, 161–168.
- Tyagi, B.; Kumar, N. (2021). Bioremediation: Principles and Applications in Environmental Management. In: *Bioremediation for environmental sustainability*. Elsevier, pp. 3–28.
- Tripathi, S., Sanjeevi, R., Anuradha, J., Chauhan, D. S., Rathoure, A.K.. (2022). Nano-bioremediation: nanotechnology and bioremediation. In: *Research Anthology on Emerging Techniques in Environmental Remediation*. IGI Global, pp. 135–149.
- Wu, Y.; Pang, H.; Liu, Y.; Wang, X.; Yu, S.; Fu, D.; Jianrong, Chen.; Wang, X. (2019). Environmental Remediation of Heavy Metal Ions by Novel-Nanomaterials: A Review. *Environ. Pollut.* **246**, 608–620.
- Bhatt, P.; Pandey, S.C.; Joshi, S.; Chaudhary, P.; Pathak, V.M.; Huang, Y.; Wu, X.; Zhou, Z.; Chen, S. (2022). Nanobioremediation: A Sustainable Approach for The Removal of Toxic Pollutants from the Environment. *J. Hazard. Mater.* **427**, 128033.
- Shahi, M.P.; Kumari, P.; Mahobiya, D.; Shahi, S.K. (2021). Nano-bioremediation of Environmental Contaminants: Applications, Challenges, and Future Prospects. In: *Bioremediation for Environmental Sustainability*. Elsevier, pp. 83–98.
- Ijaz, I.; Gilani, E.; Nazir, A.; Bukhari, A. (2020). Detail Review on Chemical, Physical and Green Synthesis, Classification, Characterizations and Applications of Nanoparticles. *Green Chem. Lett. Rev.* **13**, 223–245.
- Noman, M.; Shahid, M.; Ahmed, T.; Niazi, M.B.K.; Hussain, S.; Song, F. (2020). Use of Biogenic Copper Nanoparticles Synthesized from A Native *Escherichia* sp. As Photocatalysts for Azo Dye Degradation and Treatment of Textile Effluents. *Environ. Pollut.* **257**, 113514.
- Goutam, S.P.; Saxena, G. “Biogenic Nanoparticles For Removal Of Heavy Metals And Organic Pollutants From Water And Wastewater: Advances, Challenges And Future Prospects,” In *Bioremediation For Environmental Sustainability: Toxicity, Mechanisms Of Contaminants Degradation, Detoxification And Challenges*, Eds G. Saxena, M. Shah, And V. Kumar (Amsterdam: Elsevier Science), 2021, 623–636.
- Hsueh, C.C.; Chen, C.T.; Hsu, A.W.; Wu, C.C.; Chen, B.Y. (2017). Comparative Assessment of Azo Dyes and Nitroaromatic Compounds Reduction Using Indigenous Dye-Decolorizing Bacteria. *J. Taiwan Inst. Chem. Eng.* **79**, 134–140.
- Slavin, Y.N.; Asnis, J.; Hafeli, U.O.; Bach, H. (2017). Metal Nanoparticles: Understanding the Mechanisms Behind Antibacterial Activity. *J. Nanobiotechnol.* **15**, 65.
- Singh, J.; Dutta, T.; Kim, K.-H.; Rawat, M.; Samddar, P.; Kumar, P. (2018). ‘Green’ synthesis of Metals and Their Oxide Nanoparticles: Applications For Environmental Remediation. *J. Nanobiotechnol.* **16**, 1–24.
- Mughal, B.; Zaidi S.Z.J.; Zhang, X.; Hassan, S.U. (2021). Biogenic nanoparticles: Synthesis, Characterisation and Applications. *Appl. Sci.* **11**, 2598.
- Gupta, R.; Padmanabhan, P. (2018). Biogenic Synthesis and Characterization of Gold Nanoparticles by a Novel Marine Bacteria *Marinobacter algicola*: Progression from

- Nanospheres to Various Geometrical Shapes. *J. Microbiol. Biotech. Food. Sci.* **8**, 732–737.
19. Patil, M.P.; Kang, M.J.; Niyonizigiye, I.; Singh, A.; Kim, J.O.; Seo, Y.B.; Kim, G.D. (2019). Do Extracellular Synthesis of Gold Nanoparticles using the Marine Bacterium *Paracoccus haundensis* BC74171T and Evaluation Of Their Antioxidant Activity and Antiproliferative Effect on Normal and Cancer Cell Lines. *Colloids Surf. B Biointerfaces* **183**, 110455.
 20. Khan, N.T.; Khan, M.J.; Jameel, J.; Jameel, N.; Rheman, S.U.A. (2017). An Overview: Biological Organisms that Serves as Nanofactories for Metallic Nanoparticles Synthesis and Fungi Being the Most Appropriate. *Bioceram. Dev. Appl.* **7**, 1000101.
 21. Noor, S.; Shah, Z.; Javed, A.; Ali, A.; Hussain, S.B.; Zafar, S.; Ali, H.; Muhammad, S.A.A. (2020). Fungal Based Synthesis Method for Copper Nanoparticles with the Determination of anticancer, antidiabetic and Antibacterial Activities. *J. Microb. Met.* **174**, 105966.
 22. Dhas, T.S.; Kumar, V.G.; Karthick, V.; Angel, K.J.; Govindaraju, K. (2014). Facile Synthesis of Silver Chloride Nanoparticles using Marine Alga and its Antibacterial Efficacy. *Spectrochim. Acta A Mol. Biomol. Spectrosc.* **120**, 416–420.
 23. Skrotska, O.; Kharchenko, Y.; Laziuka, Y.; Marynin, A.; Kharchuk, M. Biosynthesis and Characteristics of Silver Nanoparticles Obtained using *Saccharomyces cerevisiae* M437. *Ukrainian. Food. J.* 2021,10, 615–631.
 24. Salem, S.S. (2022). Baker's Yeast-Mediated Silver Nanoparticles: Characterisation and Antimicrobial Biogenic Tool for Suppressing Pathogenic Microbes. *BioNanoScience* **12**, 1220–1229.
 25. Kim, D.Y.; Kim, M.; Sung, J.S.; Koduru, J.R.; Nile, S.H.; Syed, A.; Bahkali, A.H.; Seth, C.S.; Ghodake, G.S. (2024). Extracellular Synthesis of Silver Nanoparticle Using Yeast Extracts: Antibacterial and Seed Priming Applications. *Appl. Microbiol. Biotechnol.* **108**, 150.
 26. Salem, S.S. (2022). Bio-fabrication of Selenium Nanoparticles Using Baker's Yeast Extract and Its Antimicrobial Efficacy on Food Borne Pathogens. *Appl. Biochem. Biotechnol.* **194**, 1898–1910.
 27. Salwan, R.; Sharma, V. (2020). Molecular and Biotechnological Aspects of Secondary Metabolites in Actinobacteria. *Microbiol. Res.* **231**, 126374.
 28. Jose, P.A.; Maharshi, A.; Jha, B. (2021). Actinobacteria in Natural Products Research: Progress and Prospects. *Microbiol. Res.* **246**, 126708.
 29. Bennur, T.; Khan, Z.; Kshirsagar, R.; Javdekar, V.; Zinjarde, S. (2016). Biogenic Gold Nanoparticles from the Actinomycete *Gordonia amarae*: Application in Rapid Sensing Copper Ions. *Sens. Actuators B: Chem.* **233**, 684–690.
 30. Bhardwaj, D.; Singh, R. (2021). Green Biomimetic Synthesis of Ag–TiO₂ Nanocomposite using *Origanum majorana* Leaf Extract Under Sonication and Their Biological Activities. *Bioresour. Bioprocess.* **8**, 1.
 31. Park, Y.; Hong, Y.; Weyers, A.; Kim, Y.; Linhardt, R. (2011). Polysaccharides and Phytochemicals: A Natural Reservoir for The Green Synthesis of Gold and Silver Nanoparticles. *IET. Nanobiotechnol.* **5**, 69–78.
 32. Moulton, M.; Braydich-Stolle, L.; Nadagouda, M.; Kunzelman, S.; Hussain, S.; Varma, R. (2010). Synthesis, Characterization and Biocompatibility of “Green” Synthesized Silver Nanoparticles Using Tea Polyphenols. *Nanoscale* **2**, 763–770.
 33. Miu, B.A.; Dinischiotu, A. (2022). New Green Approaches in Nanoparticles Synthesis: An Overview. *Molecules* **27**, 6472.
 34. Velusamy, P.; Kumar, G.V.; Jeyanthi, V.; Das, J.; Pachiappan, R. (2016). Bio-inspired Green Nanoparticles: Synthesis, Mechanism, and Antibacterial Application. *Toxicol. Res.* **32**, 95–102.
 35. Ghoneim, M.M.; El-Desoky, H.S.; El-Moselhy, K.M.; Amer, A.; Abou El-Naga, E.H.; Mohamedein, L.I.; Al-Prol, A.E. (2014). Removal of Cadmium From Aqueous Solution Using Marine Green Algae *Ulva lactuca*. *Egypt. J. Aquat. Res.* **40**, 235–242.
 36. Alprol, E.A.; El-Metwally, E.; Amer, A. (2019). *Sargassum latifolium* as Eco-Friendly Materials for Treatment of Toxic Nickel (II) and Lead (II) Ions from Aqueous Solution. *Egypt. J. Aquat. Biol. Fish.* **23**, 285–299.
 37. Rego, R.M.; Kurkuri, M.D.; Kigga, M. A. (2022). Comprehensive Review on Water Remediation using UiO-66 MOFs and Their Derivatives. *Chemosphere* **302**, 134845.
 38. AlNadhari, S.; Al-Enazi, N.M.; Alshehrei, F.; Ameen, F. (2021). A Review on Biogenic Synthesis of Metal Nanoparticles Using Marine Algae and Its Applications. *Env. Res.* **194**, 110672.
 39. Mukherjee, A.; Sarkar, D.; Sasmal, S. (2021). A Review of Green Synthesis of Metal Nanoparticles Using Algae. *Front. Microbiol.* **12**, 693899.
 40. Borah, D.; Das, N.; Das, N.; Bhattacharjee, A.; Sarmah, P.; Ghosh, K.; Chandel, M.; Rout, Pandey, P.; Ghosh, N.N.; Bhattacharjee, C.R. (2020). Alga-Mediated Facile Green Synthesis of Silver Nanoparticles: Photophysical, Catalytic and Antibacterial Activity. *Appl. Organomet. Chem.* **34**, e5597.
 41. El-Sheekh, M.M.; El-Kassas, H.Y.; Shams El-Din, N.G.; Eissa, D.I.; El-Sherbiny, B.A. (2021). Green Synthesis, Characterization Applications of Iron Oxide Nanoparticles for Antialgal and Wastewater Bioremediation Using Three Brown Algae. *Int. J. Phytoremed.* **23**, 1538–1552.
 42. Adenigba, V.O.; Omomowo, I.O.; Oloke, J.K.; Fatukasi, B.A.; Odeniyi, M.A.; Adedayo, A.A. (2020). Evaluation of Microalgal-Based Nanoparticles in the Adsorption of Heavy Metals from Wastewater. *IOP Conf. Ser.: Mater. Sci. Eng.* **805**, 012030.
 43. El-Sheekh, M.M.; Deyab, M.A.; Hassan, N.I.; Abu Ahmed, S.E. (2023). Bioremediation of Malachite Green Dye Using Sodium Alginate, *Sargassum latifolium* Extract, and Their Silver Nanoparticles. *BMC. Chem.* **17**, 108.
 44. Mandal, R.P.; Sekh, S.; Sarkar, N.S.; Chattopadhyay, D.; De, S. (2016). Algae Mediated Synthesis of Cadmium Sulphide Nanoparticles and Their Application in Bioremediation. *Mater. Res. Express* **3**, 055007.
 45. Demirel, İ.T.; Akar, B.; Baltacı, C.; Karpuz, Ö.; Gülbahar, E. (2024). Biogenic Iron Oxide Nanoparticles Based on Algal Biofilm Formed in the Wastewater Treatment Plant and Their Dye Removal Performance. *J. Anat. Environ. Anim. Sci.* **9**, 174–183.
 46. Mansour, A.T.; Alprol, A.E.; Ashour, M.; Ramadan, K.M.; Alhajji, A.H.; Abualnaja, K.M. (2022). Do Red Seaweed Nanoparticles Enhance Bioremediation Capacity of Toxic Dyes From Aqueous Solution?. *Gels* **8**, 310.
 47. Ikhumetse, A.A.; Abioye, O.P.; Kovo, A.S.; Ijah, U.J.J. (2025). Biosynthesis of Silver Nanoparticles using *Macroccoccus caseolyticus* Strain AgD Isolated from Crude Oil-Contaminated Water Samples and Their Application in Remediation of Crude Oil Contamination in the Niger Delta Aquatic Environment. *Environ. Nanotechnol. Monit. Manag.* **23**, 101057.
 48. El-Sheekh, M.M.; Shaaban, M.T.; Goda, A.; Morsi, H.H. (2025). Green Synthesis of Iron Oxide Nanoparticles using *Lyptolyngbya foveolarum* and *Azospirillum brasilense* for Wastewater Treatment. *Int. J. Environ. Sci. Technol.* **22**, 9933–9948.
 49. Martins, M.; Mourato, C.; Sanches, S.; Noronha, J.P.; Crespo, M.B.; Pereira, I.A. (2017). Biogenic Platinum and Palladium Nanoparticles as New Catalysts for the Removal of Pharmaceutical Compounds. *Water Res.* **108**, 160–168.

50. Uba, B.O.; Obiefuna, G.O. (2023). Aerobically Enhanced Nano-Bioremediation of Diesel Oil Contaminated Soil and Water Using Myco-Synthesized Silver Nanoparticle as Biostimulating Agent. *Sci. World J.* **18**, 75–82.
51. Darwesh, O.M.; Li, H.; Matter, I.A. (2023). Nano-Bioremediation of Textile Industry Wastewater Using Immobilized CuO-NPs Myco-Synthesized by a Novel Cu-resistant *Fusarium oxysporum* OSF18. *Environm. Sci. Pollut. Res.* **30**, 16694–16706.
52. Darwesh, O.; Shalapy, M.; Abo-Zeid, A.; Mahmoud, Y. (2021). Nano-bioremediation of Municipal Wastewater Using Myco-Synthesized Iron Nanoparticles. *Egypt. J. Chem.* **64**, 2499–2507.
53. Mohammed, A.H.; Mhammedsharif, R.M.; Jalil, P.J.; Mhammedsharif, S.M.; Mohammed, A. S. (2024). Comparative Study on the Biosynthesis of Magnetite Nanoparticles using *Aspergillus elegans* Extract and their Efficacy in Dye Degradation Versus Commercial Magnetite Nanoparticles. *Heliyon* **10**, 24.
54. Vinayagam, Y. (2024). Mycosynthesis of TiO₂ Nanoparticles using *Aspergillus penicillioides* for Toxic Metal Removal and Photocatalytic Applications. *J. Water Proc. Eng.* **67**, 106279.
55. Gupta, S.; Ravi, R.K.; Pathak, B. (2024). Photocatalytic Removal of Anthracene using Zinc Oxide Nanoparticles Synthesized by *Fusarium proliferatum* WC416. *Geomicrobiol. J.* **41**, 72–81.
56. Mani, V.M.; Mohammedbasha, M.; Sabarathinam, S.; Umesh, M.; Paramasivam, D. (2025). Nanoremediation of Groundwater Contaminants Through Mycosynthesized CuONPs and ZnONPs. *BioNanoScience* **15**, 175.
57. Polli, A.D.; Verci Junior, A.D.O.; Ribeiro, M.A.S.; Polonio, J.C.; Rosini, B.; Oliveira, J.A.S.; Bini, R.D.; Golias, H.C.; Fávoro-Polonio, C.Z.; Orlandelli, R.C.; Vicentini, V.E.P.; Cotica, L.F.; Peralta, R.M.; Pamphile, J.A.; Azevedo, J.L. (2023). Synthesis, Characterization, and Reusability of Novel Nanobiocomposite of Endophytic Fungus *Aspergillus flavus* and Magnetic Nanoparticles (Fe₃O₄) With Dye Bioremediation Potential. *Chemosphere* **340**, 139956.
58. El-Shanshoury, A.E.R.; Metwally, M.A.E.A.; Allam, N.G. et al. (2025). Nano-bioremediation of Metal-Polluted Industrial Wastewater Using Myco-Synthesized Iron Oxide Nanoparticles Derived From *Aspergillus niger* AUMC. 16028. *Sci. Rep.* **15**, 35008.
59. Mohammed, Azhin H. et al. (2024). Comparative Study on the Biosynthesis of Magnetite Nanoparticles Using *Aspergillus elegans* Extract and Their Efficacy in Dye Degradation Versus Commercial Magnetite Nanoparticles. *Heliyon* **10**, e40747.
60. Nabikhan, A.; Rathinam, S.; Kandasamy, K. (2018). Biogenic Gold Nanoparticles for Reduction of 4-nitrophenol to 4-aminophenol: An Eco-Friendly Bioremediation. *IET Nanobiotech.* **12**, 479–483.
61. López-Miranda, J.L.; Esparza, R.; Rosas, G.; Pérez, R.; Estévez-González, M. (2019). Catalytic and Antibacterial Properties of Gold Nanoparticles Synthesized by a Green Approach for Bioremediation Applications. *3 Biotech.* **9**, 135.
62. Guo, Y.; Huang, C.; Pitcheri, R.; Shekhar, B.; Radhalayam, D.; Roy, S.; Kummara, M.R.; Karim, M.R. (2025). Bio-green Synthesis of Bismuth Oxide Nanoparticles using Almond Gum for Enhanced Photocatalytic Degradation of Water Pollutants and Biocompatibility. *Int. J. Biolog. Macromol.* **300**, 140222.
63. Upadhyay, L.S.B.; Tirkey, A.; Bhagat, P.; Singh, S.K.; Mishra, A. (2025). Green Synthesis of Copper Oxide Nanoparticles Using *Solanum tuberosum* Extract to Mediate Photocatalytic Degradation of Methylene Blue. *Plasmonics* **20**, 8279–8294.
64. Murgueitio, E.; Cumbal, L.; Abril, M.; Izquierdo, A.; Debut, A.; Tinoco, O. (2018). Green Synthesis of Iron Nanoparticles: Application on The Removal of Petroleum Oil from Contaminated Water and Soils. *J. Nanotech.* **2018**, 4184769.
65. Muthukumar, B.; Duraimurugan, R.; Parthipan, P.; Rajamohan, R.; Rajagopal, R.; Narenkumar, J.; Rajasekar, A.; Malik, T. (2024). Synthesis and Characterization of Iron Oxide Nanoparticles from *Lawsonia inermis* and its Effect on the Biodegradation of Crude Oil Hydrocarbon. *Sci. Rep.* **14**, 11335.
66. Vasantharaj, S.; Sathiyavimal, S.; Senthilkumar, P.; LewisOscar, F.; Pugazhendhi, A. (2019). Biosynthesis of Iron Oxide Nanoparticles using Leaf Extract of *Ruellia tuberosa*: Antimicrobial Properties and Their Applications in Photocatalytic Degradation. *J. Photochem. Photobiol. B: Biol.* **192**, 74–82.
67. Munir, N.; Chaudhary, A.; Hanif, M.; Dias, D.A.; El-Sheikh, M.A.; Abideen, Z. (2025). Co-application of Apple Peel Nanoparticles and Functional Halophytic Biochar Improve the Remediation of Hazardous Cr and Pb for Environmental Safety. *Int. J. Environm. Res.* **19**, 1–26.
68. Rajendran, A.; Alsawalha, M.; Alomayri, T. (2021). Biogenic Synthesis of Husked Rice-Shaped Iron Oxide Nanoparticles using Coconut Pulp (*Cocos nucifera* L.) Extract for Photocatalytic Degradation of Rhodamine B Dye and Their *In Vitro* Antibacterial and Anticancer Activity. *J. Saudi Chem. Soc.* **25**, 101307.
69. Nimmi, O.S.; Shilpa, H.; Sameena, Y.; Josephine, C.R.; Sharmila, V.; Kanmani, S.S. (2024). Efficacy of Nanoparticle Synthesized Spinach Variety In Bioremediation Of Copper From Contaminated Waters. *World J. Pharm. Pharmaceut. Sci.* **13**, 664–683.
70. El-Sheekh, M.M.; Shaaban, M.T.; Goda, A.; Morsi, H.H. (2025). Green Synthesis of Iron Oxide Nanoparticles using *Lyptolyngbya foveolarum* and *Azospirillum brasilense* for Wastewater Treatment. *Int. J. Environm. Sci. Tech.* **22**, 9933–9948.
71. Abel, S.K.; Amirtharajan, S.; Mahalingam, A.; Baskaran, S.; Pandurengan, S. (2025). Green Synthesis of rGO/MgO Nanocomposite using *Hylocereus polyrhizus* Peel Extract for Antibacterial Activity and Photocatalytic Dye Degradation Study. *Chem. Physics Imp.* **10**, 100885.
72. Sivarajan, Y.; Ishak, K.A.; Yaacob, J.S. (2025). Green Synthesis of Tin Oxide (SnO₂) Nanoparticles Using Ginger Extracts for Photocatalytic Degradation of Organic Dyes in Wastewater. *Appl. Biochem. Biotechnol.* **197**(9), 5668–5693.
73. PalajonnalaNarasaiah, B.; Banoth, P.; Bustamante Dominguez, A.G.; Mandal, B.K.; Kumar, C.K.; Barnes, C.H.; De Los Santos Valladares, L.; Kollu, P. (2022). Biogenic Photo-Catalyst TiO₂ Nanoparticles for Remediation of Environment Pollutants. *ACS Omega* **7**, 26174–26189.
74. Yuan, Y.; Wu, Y.; Suganthy, N.; Shanmugam, S.; Brindhadevi, K.; Sabour, A.; Alshiekheid, M.; Chi, N.T.L.; Pugazhendhi, A.; Shanmuganathan, R. (2022). Biosynthesis of Zirconium Nanoparticles (ZrO₂ NPs) by *Phyllanthus niruri* Extract: Characterization and Its Photocatalytic Dye Degradation Activity. *Food Chem. Toxic.* **168**, 113340.
75. Vasantharaj, S.; Sathiyavimal, S.; Senthilkumar, P.; Kalpana, V.N.; Rajalakshmi, G.; Alsehli, M.; Pugazhendhi, A. (2021). Enhanced Photocatalytic Degradation of Water Pollutants Using Bio-Green Synthesis of Zinc Oxide Nanoparticles (ZnO NPs). *J. Environm. Chem. Eng.* **9**, 105772.
76. Mashentseva, A.A.; Seitzhaphar, N.; Barsbay, M.; Aimanova, N.A.; Alimkhanova, A.N.; Zheltov, D.A.; Zhumabayev, A.M.; Temirgaziev, B.S.; Almanov, A.A.; Sadyrbekov, D.T. (2023). Adsorption Isotherms and Kinetics for Pb (ii) Ion Removal from Aqueous Solutions with Biogenic Metal Oxide Nanoparticles. *RSC Advance* **13**, 26839–26850.
77. Kaur, H.; Sharma, A.; Anand, K.; Panday, A.; Tagotra, S.; Kakran, S.; Singh, A.K.; Alam, M.W.; Kumar, S.; Bouzid, G.; Dalal, J. (2025). Green synthesis of ZnO nanoparticles using *E. cardamomum* and zinc nitrate precursor: a dual-functional

- material for water purification and antibacterial applications. *RSC Advance* **15**, 16742–16765.
78. Aoun, A.; Ben Mya, O.; Barani, D. (2025). Green Synthesis of Zinc Oxide Nanoparticles using *Eucalyptus* leaf Extract for Effective Calcium Removal From Groundwater. *Biomass Conv. Bioref.* **15**, 12581–12590.
79. Vinayagam, Y.; Venkatraman, G.; Rajeswari, V.D. (2025). Sustainable Treatment of Glass Industry Wastewater using Biogenic Zinc Oxide Nanoparticles: Antibacterial and Photocatalytic Efficacy. *Int. Biodeterior. Biodegrad.* **200**, 106036.
80. Ijaz, I.; Gilani, E.; Nazir, A.; Bukhari, A. (2020). Detail Review On Chemical, Physical And Green Synthesis, Classification, Characterizations And Applications of Nanoparticles. *Green. Chem. Lett. Rev.* **13**, 223–245.
81. Rana, A.; Yadav, K.; Jagadevan, S. (2020). A Comprehensive Review on Green Synthesis of Nature-Inspired Metal Nanoparticles: Mechanism, Application and Toxicity. *J. Clean. Prod.* **272**, 122880.
82. Misra, M.; Ghosh Sachan, S. (2022). Nanobioremediation of Heavy Metals: Perspectives and Challenges. *J. Basic. Microbiol.* **62**, 428–443.
83. Kitture, R.; Koppikar, S. J.; Kaul-Ghanekar, R.; Kale, S.N. (2011). Catalyst Efficiency, Photostability and Reusability Study of ZnO Nanoparticles in Visible Light For Dye Degradation. *J. Phys. Chem. Solids.* **72**, 60–66.
84. S. Ying et al. (2022). Green Synthesis of Nanoparticles: Current Developments and Limitations. *Environ. Technol. Innov.* **26**, 102336.
85. Singh, A.; Tyagi, P.; Ranjan, R.; Sushkova S.N.; Minkina, T.; Burachevskaya, M.; Rajput, V.D. (2023). Bioremediation of Hazardous Wastes Using Green Synthesis of Nanoparticles. *Processes* **11**, 141.